

ROLLER BEARING

BACKGROUND OF THE INVENTION

Field of the Invention

5 This invention relates to a roller bearing, and particularly to a roller bearing ~~in a bearing~~ for a spindle which is a portion of the constituent parts of various motors or the like and which ^{exhibits} is excellent in bearing characteristic and ^a is greatly mitigated ^{susceptibility} in fretting corrosion created by repeated shock and swing attributable to extraneous vibration as during conveyance.

Related Background Art

15 The industry related to electrical instruments is ~~high in the speed~~ of technological innovation as compared with the other industrial fields. The available periods of ^{a particular} types of machines are short, and ~~moreover~~ ^{introducing} new types of machines ~~having introduced~~ new techniques (smaller electric power consumption, higher responsiveness, higher accuracy, compactness, etc.) are ^{being} developed one after another.

20 ~~The~~ ^{The} ~~Now~~ ^{Now} the bearings for the spindles of various motors or the like have been ^{required to provide} made higher in speed ^{capability} with the development of the new types of machines as

25 described above, and lower torque has come to be required of them for the purpose of smaller electric power consumption. In the roller bearings used for the

spindles according to the prior art, there have been
adopted a lubricating ^{portion} ~~system~~ filled with grease, and a
method of applying lubricating oil to the raceway
surface or the like of the bearing and further ^{enclosing} ~~enclose~~
grease therein. At present, for the purpose of lower
torque ^{to accommodate} ~~resulting from~~ the requirement for smaller
electric power consumption as described above, an
amount of grease is ^{reduced} ~~less~~, and as lubricating oil
applied to the raceway surface or the like of the
bearing, many lubricating oils of low dynamic viscosity
(dynamic viscosity of 5 to 15 mm²/s at 40°C) are used
for rust prevention and ~~in the~~ low torque.

^{The Shipment}
~~Now, the inland conveyance~~ of various motors often
takes place on land, and they are transported ^{in an} ~~under~~
^{in which they are}
environment ^{apt} to be subjected to extraneous
vibrations. By these extraneous vibrations, the
bearings for the spindles suffer from axial ^{vibration} ~~excitation~~,
or repeated circumferential swing depending on the way
in which the instruments are placed.

When such axial vibration or circumferential
swinging movement is repeated, a bearing for a spindle
^{designed for} ~~directed~~ to low torque may ^{be subjected to} ~~suffer from the possibility~~
~~of creating~~ fretting corrosion on the raceway surfaces
of the outer race and inner race thereof, and the
contact surfaces of the rolling elements thereof.
because the quantity of grease is small and ~~moreover~~
the strength of oil film is low in lubricating oil of

low dynamic viscosity.

a 5 The creation of fretting corrosion may result in an increase in the sound and vibration of the bearing and may also pose a serious ^{hindrance to} ~~problem in a~~ further improvement in required accuracy.

a 10 So, the present invention has been made in order to prevent the creation of fretting corrosion ~~which may be created~~ in a bearing for a spindle during the conveyance of various motors as noted above, and ^{a principal} ~~the~~ object thereof is to provide a fretting-resisting roller bearing which is not adversely affected in its characteristics and achieves a higher temperature and a higher speed as well as a longer life.

15 SUMMARY OF THE INVENTION

a 20 To achieve the above object, the roller bearing of the present invention is a roller bearing comprised of a plurality of rolling elements held between an inner race and an outer race with a cage interposed therebetween, characterized in that ^{an} ~~the~~ oil film of lubricating oil of which the dynamic viscosity at 40°C is 20 to 150 mm²/s is formed on the raceway surfaces of the inner and outer races, the cage and the rolling elements and grease is enclosed.

25 The roller bearing of the present invention is heightened in the dynamic viscosity of the lubricating oil and the strength of the oil film with a view to

09199447-11598

improve the fretting-resisting property during the conveyance of various motors.

Also, for example, the rolling elements are made of ceramics or a super-hard alloy of which the Vickers hardness is 1300 or greater, and the outer race and inner race are made of steel, ^{• Preferably,} and a material differing from that of the outer race and inner race is used as the material of the rolling elements and the hardness thereof is increased, whereby not only fretting corrosion can be suppressed by the prevention of the adhesion phenomenon between the members (the raceway surfaces of the outer and inner races and the rolling elements) and the decrease in Hertzian contact area due to the difference in Young's modulus, but also a good function is obtained even under use conditions of high temperature and high-speed rotation.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a graph showing the acceleration signal execution values of each embodiment and each comparative example.

Fig. 2 is a graph showing the rotation torques of each embodiment and each comparative example.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Some embodiments of the fretting-resisting roller bearing of the present invention will

09199447 "112598"

hereinafter be described in detail.

2
5 The fretting-resisting roller bearing of the present invention is a roller bearing comprised of a plurality of rolling elements held between an inner race and an outer race with a cage interposed therebetween, wherein ^{an} ~~the~~ oil film of lubricating oil of which the dynamic viscosity at 40°C is 20 to 150 mm²/s is formed on the raceway surfaces of the inner and outer races, the cage and the rolling elements, and
10 grease is enclosed.

When the dynamic viscosity of the lubricating oil at 40°C is less than 20 mm²/s, the strength of the oil film is low and fretting corrosion is liable to be created by extraneous vibrations. When conversely, the
15 dynamic viscosity at 40°C is higher than 150 mm²/s, rotation torque increases because the dynamic viscosity of the lubricating oil is high. Further, to reduce fretting corrosion, it is preferable that the dynamic viscosity at 40°C be 40 mm²/s or greater.

20 While the lubricant composition used as the lubricating oil is not particularly limited, it may be composed of base oil and various additives mentioned below, whereby there is formed lubricating oil film having a fretting-resisting property and a rust
25 prevention property and suitable for use at a high temperatures and high speeds. In the embodiments as described hereinafter, the composition of the additives

09199447 112598

2 can be selected in accordance with ^{use} ~~using~~ ^{the} conditions of
bearings if control of fretting corrosion is maintained,
2 and ~~functions of~~ anti-rust properties and additional
^{also be provided} properties can ~~be combined in need~~. Particularly, if
5 the higher anti-rust properties are required under some
^{use} ~~using~~ conditions, preferably ^{containing a} the lubricant oil may be
a anti-rust lubricant oil ~~combined with the~~ rust
prevention agent, which has high anti-rust properties.
a (Base Oil)

10 Regarding the base oil, as ester oil, use may
preferably be made of diester oil obtained from the
reaction of dibasic acid and branch alcohol, aromatic
ester oil obtained from the reaction of aromatic
tribasic acid and branch alcohol, or hindered ester oil
15 obtained from the reaction of polyatomic alcohol and
monobasic acid.

As diester oil, mention may be made of dioctyl
adipate (DOA), diisobutyl adipate (DIBA), dibutyl
adipate (DBA), dioctyl azelate (DOZ), dibutyl sebacate
20 (DBA), dioctyl sebacate (DOS), methyl acetyl recinolate
(MAR-N) or the like.

As aromatic ester oil, mention may be made of
trimellitic acid ester, trioctyl trimellitate (TOTM),
tridecyl trimellitate, tetraoctyl pyromellitate or the
25 like.

a As hindered ester oil, mention may be made of one
obtained by polyatomic alcohol and monobasic acid ~~shown~~.

09159447 112599

~~below~~ being suitably reacted with each other.

Monobasic acid to be reacted with polyatomic alcohol may be single or plural. Further, it may be used as complex ester which is oligoester of polyatomic alcohol and mixed aliphatic acid of dibasic acid and monobasic acid.

As polyatomic alcohol, mention may be made of trimethylol propane (TMP), pentaerythritol (PE), dipentaerythritol (DPE), neopentyl glycol (NPG), 2-methyl-2-propyl-1,3-propane (MPPD) or the like.

As monobasic acid, use is made chiefly of univalent aliphatic acid of C_4 to C_{18} . Specifically, mention may be made of acetic acid, valerianic acid, caproic acid, caprylic acid, enanthic acid, pelargonic acid, capric acid, undecanic acid, laurylic acid, mistiric acid, palmitic acid, beef fatty acid, stearic acid, caproleic acid, undecylenic acid, linder acid, tudu acid, fiseterinic acid, milistolenic acid, palmitoleic acid, petroserine acid, oleic acid, elaiolic acid, asclepic acid, vaccenic acid, sorbic acid, linoleic acid, linolenic acid, sabineic acid, recinoleic acid, or the like.

As synthetic hydrocarbon oil, there is phenyl ether oil in which (di)alkyl chain of C_{12} to C_{20} of disphenyl, triphenyl and tetraphenyl was derived.

Taking lower evaporation and longer life into account, it is preferable that ester oil be chosen from

0919447 112599
065211 24465760

aromatic ester oil and hindered ester oil and be used singly or mixedly. Particularly TOTM is readily available and is excellent in a low evaporating property, a lubricating property, etc. Also, (di)alkyl polyphenyl ether oil is preferable as ether oil. Fluorophosphazene oil can also be suitably used.

Also, by adding additives such as rust prevention agents, oily agents and oxidation preventing agents mentioned below, lubricating performance (fretting-resisting property or the like) and ^{durability} ~~endurable performance~~ can be ^{enhanced} ~~more improved~~.
(Rust ^{Prevention} ~~prevention~~ Agent)

Organic sulfonic acid metal or ester is preferable as a rust prevention agent. As organic sulfonic acid salt, use is made, for example, of dinonyl naphthalene sulfonic acid and heavy alkyl benzene sulfonic acid, and as the metal salt thereof, there is calcium sulfonate, barium sulfonate, sodium sulfonate or the like.

As ester, in sorbitan derivative, there is sorbitan monolaurate, sorbitan tristearate, sorbitan monooleate, sorbitan trioleate or the like as the partial ester of polybasic carboxylic acid and polyatomic alcohol. As alkyl ester type, there is polyoxyethylene laurate, polyoxyethylene oleate, polyoxyethylene stearate or the like.

As these rust prevention agents, organic sulfonic

00199447 112598

acid metal salt and ester can be used singly or as a mixture. Taking it into account to improve the rust prevention property and suppress fretting corrosion, ester polyoxyethylene sorbitan laurate is high in dissolving property and is suitably used as sulfonic acid metallic salt such as calcium sulfonate, and fluorophosphazene oil.

(Oily Agent)

mix ag → As an ^{*oily*} ~~oil~~ agent, ^{*as*} oleic acid, stearic acid or the like as higher fatty acid, lauryl alcohol, oleyl alcohol or the like as higher alcohol, stearyl amine, cetyl amine or the like as amine. ^{*These*} ~~these~~ can be used singly or mixedly.

~
(Oxidation Preventing Agent)

15 As an oxidation preventing agent, a nitrogen containing compound oxidation preventing agent and a phenol oxidation preventing agent may preferably be used singly or as a mixture.

20 As the nitrogen containing compound oxidation preventing agent, there is phenyl α naphthylamine, diphenylamine, phenylene diamine, oleyl amideamine, phenothiazine or the like.

25 As a phenol oxidation preventing agent, there is hindered phenol such as p-t-butyl-phenyl salicylate, 2,6-di-t-butyl-p-phenyl phenol, 2,2'-methylenebis-(4-methyl-6-t-octyl phenol), 4,4'-butyrydenbis-6-t-butyl-m-cresol, tetrakis[methylene-3-(3',5'-di-t-butyl-

00199447-112598
SECRET

4'-hydroxyphenyl)propionate]methane, 1,3,5-trimethyl-
2,4,6-tris(3,5-di-t-butyl-4-hydroxylbenzil)benzene,
n-octadecyl- β -(4'-hydroxy-3',5'-di-t-
butylphenyl)propionate, 2-n-octylthio-4,6-di(4'-
5 hydroxy-3',5'-di-t-butyl)phenoxy-1,3,5-triazine,
4,4'-thiobisu-[6-t-butyl-m-cresol],
2-(2'-hydroxy-3'-t-butyl-5'-methylphenyl)-5-
chlorobenzotriazole or the like.

(Extreme Pressure Agent)

10 As an extreme pressure agent, use can be made of
organic metallic salt such as molybdenum thiocarbamate,
molybdenum dithio phosphate, zinc diocarbamate, zinc
dithiophosphate or the like.

(Corrosion Preventing Agent)

15 As a corrosion preventing agent, mention may be
made of phosphoric acid ester, phosphorous acid ester
or the like. Particularly, molybdenum dithiocarbamate
and phosphorous acid ester exhibit an excellent effect
in the fretting resisting property and ^{may} therefore be
20 ^{preferred} suitably used.

2 In addition to the foregoing agents, a friction
preventing agent, a viscosity index improving agent or
the like may be contained in the lubricating oil.
These may all be conventional agents.

25 Regarding the base oil and additive of the grease
enclosed in the above-described fretting-resisting
roller bearing of the present invention, use may be

091944-1259
SECRET

made of ones similar to the above-described lubricating oil composition of the present invention. Also, a thickness^{regulating agent} may be a conventional one such as metallic soap or urea resin, but from the viewpoint of the characteristic of the bearing for a spindle, lithium soap having an excellent characteristic in acoustic life is preferable.

In the case of the fretting-resisting roller bearing of the present invention, the contacting portions of the raceway surfaces of the outer and inner races and the rolling elements are the same material or different materials. ^{• preferably,} and when different materials are used, they are steel and ceramics or steel and a super-hard alloy. If the lubricating oil in the present invention is used, the fretting corrosion will be greatly mitigated, and further, under an environment of severe vibration condition, different materials may be small in the frictional force acting on the contacting portions as compared with steel and steel, and in these contacting portions, it is more difficult for such an injury which will lead to fretting corrosion to occur.

In the case of ceramics, the material forming the rolling elements may be silicon nitride, zirconia, alumina or the like, and in the case of a super-hard alloy, the material forming the rolling elements may be tungsten carbide or the like.

The friction characteristic on the contacting

portions of the raceways of the outer and inner races made of steel and the rolling surfaces of the rolling elements made of ceramics or a super-hard alloy is improved as compared with the friction characteristic when steel and steel contact with each other, ~~even if the combination of different materials is steel and ceramics or steel and a super-hard alloy.~~ Above all, the combination of bearing steel and silicon nitride, stainless steel and silicon nitride, bearing steel and zirconia, bearing steel and tungsten carbamate, or stainless steel and tungsten carbamate provides an excellent friction characteristic (a low friction characteristic) and is excellent in the fretting resisting property. By combining these with the above-mentioned lubricating oil, a further effect is obtained against fretting corrosion and these combinations can be preferably be used.

Description will now be made of the conditions and results of evaluation tests carried out to confirm the effect of the present invention.

[Bearing Outer Race Swing Test]

Tested bearing : 695

Frequency : 27 Hz

Angle of swing : 2°

Load (Fa) : 14.7 N

Frequency of swing : 1×10^5 times

Enclosed grease : Lithium soap grease

The above-mentioned swing test was carried out, and the acceleration of the bearing in the radial direction thereof after the test was measured and evaluation was effected.

5 A heretofore used bearing specification [Comparative Example 1] was subjected to a swing test, and comparison evaluation was effected with the bearing radial direction acceleration signal execution value after the test being 100%.

a 10 ^{Because}
~~It is because~~ the traces of minute fretting corrosion created on the inner and outer races and rolling elements of the bearing can be measured with good sensitivity, ^a ~~that~~ the bearing radial direction acceleration was used as a test evaluation item.

15 [Measurement of Rotation Torque]

Tested bearing : 695
Load (Fa) : 14.7 N
Number of revolutions : 3600 rpm

As regards the magnitude of torque, 1.2 gf·cm or
20 less was regarded as being successful.

The test conditions of each embodiment and each comparative example are as follows:

[Embodiment 1]

25 A bearing in which lubricating oil C of which the dynamic viscosity at 40°C was 90 mm²/s was formed into film on the raceway surfaces of inner and outer races, a cage and rolling elements and grease was enclosed was

0919447-1359

tested in a pre-load state under the above-mentioned conditions.

[Embodiment 2]

5 A bearing in which rolling elements were made of
silicon nitride and lubricating oil C of which the
dynamic viscosity at 40°C was 90 mm²/s was formed into
film on the raceway surfaces of inner and outer races,
a cage and rolling elements and grease was enclosed was
tested in a pre-load state under the
10 above-mentioned conditions.

[Embodiment 3]

A bearing in which rolling elements were made of
tungsten carbide of Vickers hardness 1300 and
lubricating oil C of which the dynamic viscosity at
15 40°C was 90 mm²/s was formed into film on the raceway
surfaces of inner and outer races, a cage and rolling
elements and grease was enclosed was tested in a
pre-load state under the above-mentioned conditions.

[Embodiment 4]

20 A bearing in which lubricating oil B of which the
dynamic viscosity at 40°C was 25 mm²/s was formed into
film on the raceway surfaces of inner and outer races,
a cage and rolling elements and grease was enclosed was
tested in a pre-load state under the
25 above-mentioned conditions.

[Embodiment 5]

A bearing in which rolling elements were made of

0919447-42596

silicon nitride and lubricating oil B of which the
dynamic viscosity at 40°C was 25 mm²/s was formed into
film on the raceway surfaces of inner and outer races,
a cage and rolling elements and grease was enclosed was
5 tested in a pre-load state under the
above-mentioned conditions.

[Embodiment 6]

A bearing in which rolling elements were made of
tungsten carbide of Vickers hardness 1300 and
10 lubricating oil B of which the dynamic viscosity at
40°C was 25 mm²/s was formed into film on the raceway
surfaces of inner and outer races, a cage and rolling
elements and grease was enclosed was tested in a
pre-load state under the above-mentioned conditions.

15 [Embodiment 7]

A bearing in which lubricating oil E of which the
dynamic viscosity at 40°C was 150 mm²/s was formed into
film on the raceway surfaces of inner and outer races,
a cage and rolling elements and grease was enclosed was
20 tested in a pre-load state under the
above-mentioned conditions.

[Embodiment 8]

A bearing in which lubricating oil F of which the
dynamic viscosity at 40°C was 25 mm²/s was formed into
25 film on the raceway surfaces of inner and outer races,
a cage and rolling elements and grease was enclosed was
tested in a pre-load state under the

05169447-1399
SECRET

above-mentioned conditions.

[Embodiment 9]

5 A bearing in which lubricating oil G of which the dynamic viscosity at 40°C was 90 mm²/s was formed into film on the raceway surfaces of inner and outer races, a cage and rolling elements and grease was enclosed was tested in a pre-load state under the above-mentioned conditions.

[Embodiment 10]

10 A bearing in which lubricating oil H of which the dynamic viscosity at 40°C was 120 mm²/s was formed into film on the raceway surfaces of inner and outer races, a cage and rolling elements and grease was enclosed was tested in a pre-load state under the above-mentioned conditions.

[Comparative Example 1]

20 A bearing in which lubricating oil A of which the dynamic viscosity at 40°C was 11 mm²/s was formed into film on the raceway surfaces of inner and outer races, a cage and rolling elements and grease was enclosed was tested in a pre-load state under the above-mentioned conditions.

[Comparative Example 2]

25 A bearing in which lubricating oil D of which the dynamic viscosity at 40°C was 160 mm²/s was formed into film on the raceway surfaces of inner and outer races, a cage and rolling elements and grease was enclosed was

0049447446760

tested in a pre-load state under the above-mentioned conditions.

The compositions of the lubricating oils A to H used in the above-described embodiments and comparative examples are shown in Table 1 below.

Table 1

	Lubricating Oil A	Lubricating Oil B	Lubricating Oil C	Lubricating Oil D
kind of oil	DOS	PAO	TOTM	ADE
dynamic viscosity mm ² /s (40°C)	11	25	90	160
rust prevention agent	calcium sulfonate	calcium sulfonate	calcium sulfonate	sodium sulfonate
additive	—	zinc dithiophosphate	molybdenum dithiophosphate	phosphorous acid ester

094947 445750

Table 1 (continued)

	Lubricating Oil E	Lubricating Oil F	Lubricating Oil G	Lubricating Oil H
kind of oil	MO	PET	TOTM	PAO
dynamic viscosity mm ² /s (40°C)	150	25	90	120
rust prevention agent	sodium sulfonate	calcium sulfonate	barium sulfonate	calcium sulfonate
additive	phosphorous acid	phosphorous acid ester	zinc dithiophosphate	molybenum dithiophosphate

DOS : dioctyl sebacate,

PAO : poly- α -olefin,

TOTM : trioctyl trimellitate,

ADE : alkyl diphenyl ether

MO : mineral oil

The acceleration signal execution values and rotation torques in the above-described embodiments and comparative examples are shown in the graphs of Figs. 1 and 2, respectively.

According to the fretting-resisting roller bearing of the present invention described above, there are obtained the following effects:

(1) The oil film of lubricating oil having high dynamic viscosity is formed on the raceway surfaces of the inner and outer races, the cage and the rolling elements and therefore, there can be provided a

09499447-12598

a
a
a
5 fretting-resisting roller bearing in which the strength
of the oil film is high, and the fretting-resisting
property during conveyance is improved and ~~also~~ the
various characteristics of the bearing are not
adversely affected, and which ^{further} achieves a higher
temperature and a higher speed as well as a longer
life.

06527 446760
10 (2) When the material of the rolling elements is
ceramics or a super-hard alloy of Vickers hardness 1300
or greater and the outer and inner races are made of
steel and a material differing from the material of the
outer and inner races is used as the material of the
rolling elements, the hardness thereof is increased,
whereby not only fretting corrosion can be suppressed
15 by the prevention of the adhesion phenomenon between
the members (the raceway surfaces of the outer and
inner races and the rolling elements) and the decrease
in the Hertzian contact area by the difference in
Young's modulus, but also the bearing functions well
20 even under the use conditions of high temperatures and
high-speed rotation.